

Cutback Bitumen

Type : Slow-Curing

Grade : SC-800

Standard : ASTM D 2026M - 15



Property	Min	Max	Test Method
Kinematic viscosity at 60°C [140°F], mm ² /s	800	1600	ASTM
Flash point (Cleveland open cup), °C [°F]	93	-	ASTM D92
Distillate test:			
Total distillate to 360°C [680°F], volume %	2	12	ASTM D402
Solubility, %	99		ASTM D2042
Kinematic viscosity on distillation residue at 60°C [140°F], mm ² /s	2000	16000	ASTM D2170
Asphalt residue:			
Residue of 100 penetration, %	70		ASTM D243
Ductility of 100 penetration residue at 25°C [77°F], cm	100		ASTM D113
Water, %	-	0.5	ASTM D95

Applications:
Dense-graded aggregate
Open-graded aggregate
Dense-graded aggregate

Patching, immediate use
Patching, stockpile

