

Cutback Bitumen

Type : Slow-Curing

Grade : SC-3000

Standard : ASTM D 2026M - 15



Property	Min	Max	Test Method
Kinematic viscosity at 60°C [140°F], mm ² /s	3000	6000	ASTM D2170
Flash point (Cleveland open cup), °C [°F]	107	-	ASTM D92
Distillate test:			
Total distillate to 360°C [680°F], volume %	-	5	ASTM D402
Solubility, %	99		ASTM D2042
Kinematic viscosity on distillation residue at 60°C [140°F], mm ² /s	4000	35000	ASTM D2170
Asphalt residue:			
Residue of 100 penetration, %	80		ASTM D243
Ductility of 100 penetration residue at 25°C [77°F], cm	100		ASTM D113
Water, %	-	0.5	ASTM D95

Applications:

Open-graded aggregate

Dense-graded aggregate

Patching, immediate use